

# 117001186

## EPDM 70 black perox

Rev. 03

### General Application Temperature Range

From -40°C  
To +150°C

### General Environmental Application

Water  
Ozone  
UV Rays

### Curing System

Peroxide

### Compliances

#### Disclaimer

Tests performed on test slabs. Temperatures, applications, and indications are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

### PHYSICAL AND MECHANICAL PROPRIETIES

Property	Test STD	Unit	Value
Density	ASTM D1817	g/cm3	1.18 ± 0.03
Hardness	ISO 7619	Shore A	70 ± 5
Tensile Strength	DIN 53504 S2	N/mm2	>12
Elongation	DIN 53504 S2	%	> 170

### LOW TEMPERATURE RESISTANCE

Property	Test STD	Unit	Value
TR10	ASTM D1329	°C	< -37

### COMPRESSION SET TESTS

Parameters	Test STD	Unit	Value
24h @ 200°C	ISO 815-1 A	%	< 13
72h @ 200°C	ISO 815-1 A	%	< 25

### AGEING PROPERTIES

		Standard:	
Properties	Unit	Unit	Value
Hardness	Shore A		
Tensile Strength	%		
Elongation	%		
Volume	%		
Weight	%		

		Standard:	
Properties	Unit	Unit	Value
Hardness	Shore A		
Tensile Strength	%		
Elongation	%		
Volume	%		
Weight	%		

		Standard:	
Properties	Unit	Unit	Value
Hardness	Shore A		
Tensile Strength	%		
Elongation	%		
Volume	%		
Weight	%		

		Standard:	
Properties	Unit	Unit	Value
Hardness	Shore A		
Tensile Strength	%		
Elongation	%		
Volume	%		
Weight	%		