

118001101

EPDM 80 black perox

Rev. 04

General Application Temperature Range

From -40°C
To +150°C

General Environmental Application

Water
Ozone
UV Rays

Curing System

Peroxide

Compliances

Note

**50Refr.MAN324

Disclaimer

Tests performed on test slabs. Temperatures, applications, and indications are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

PHYSICAL AND MECHANICAL PROPRIETIES

Property	Test STD	Unit	Value
Density	ASTM D1817	g/cm3	1.18 ± 0.03
Hardness	ISO 7619	Shore A	80 ± 5
Tensile Strength	DIN 53504 S2	N/mm2	>13
Elongation	DIN 53504 S2	%	> 165

LOW TEMPERATURE RESISTANCE

Property	Test STD	Unit	Value
TR10	ASTM D1329	°C	< -43

COMPRESSION SET TESTS

Parameters	Test STD	Unit	Value
24h @ 200°C	ISO 815-1 B	%	< 9
72h @ 200°C	ISO 815-1 B	%	< 12

AGEING PROPERTIES

Heat Aging - 70h @ 150°C Standard: DIN 53508

Properties	Unit	Value
Hardness	Shore A	+ 1.0
Tensile Strength	%	-10.0
Elongation	%	-15.0
Volume	%	
Weight	%	

50% Water: ** - 166h @ 150°C Standard: DIN 53521

Properties	Unit	Value
Hardness	Shore A	-4.0
Tensile Strength	%	-6.0
Elongation	%	+10.0
Volume	%	
Weight	%	

50% Water:** - 1344h @150°C Standard: DIN 53521

Properties	Unit	Value
Hardness	Shore A	-5.0
Tensile Strength	%	-9.0
Elongation	%	-6.0
Volume	%	
Weight	%	

Standard:

Properties	Unit	Value
Hardness	Shore A	
Tensile Strength	%	
Elongation	%	
Volume	%	
Weight	%	