

## Material test report VMQ 60

Colour                      Red

Property	Unit	Test method	Test parameter	Value
Hardness	Shore A	DIN 53505		60±5
Tensile strength	MPa	DIN 53504		min. 8
Ultimate elongation	%	DIN 53504		min. 300
Tear resistance	kN/m	ASTM D 624 B		min. 15
Specific gravity	g/cm <sup>3</sup>	DIN 53479		1,2 ±0,02
Compression set	%	DIN 53517	22h / 175°C	max. 40

Material approvals

FDA-compliant, 21 CFR FDA § 177.2600, SGS test report 3966415

The above indicated data were determined to the best knowledge according to modern laboratory standards on standardised test specimen. If these data are compared with data which were determined on finished parts it may come to variations.